

SAMPO MATERIAL DATA

Sampo UNI 97A

Technical properties

Property	Unit	Matrix value
Density	kg/m ³	n.v.
Shore A hardness	Shore A	95 ± 3
Shore D hardness / 15 s	Shore D	51 ± 3
Tensile strength	MPa	45
Elongation at break	%	400
Stress at 100% elongation	MPa	18
Stress at 300% elongation	MPa	n.v.
Tear strength	kN/m	n.v.
Abrasion volume loss	mm ³	n.v.
Rebound resilience	%	n.v.
Compression set / 24 h / 70 °C / 25%	%	≤ 25
Compression set / 72 h / 70 °C / 25%	%	≤ 28
Maximum temperature	°C	110
Minimum temperature	°C	-30
Vicat softening temperature / 10 N / 120 °C/h	°C	n.v.

≥ Minimum value · ≤ Maximum value · ± Tolerance · n.v. not reported. Values without limit symbols are characteristic values, not guaranteed limits.

Vicat test: force 10 N, heating rate 120 °C/h. Temperature values are application-dependent guidelines.

Data source: Sampo material data matrix, worksheet Datenmatrix, column Q. Data as of 10 September 2026.